



Leading Manufacturer of  
ELECTRICAL INSULATION MATERIALS

九江鑫星绝缘材料有限公司  
JIUJIANG XINXING INSULATION MATERIAL CO.,LTD

Email: sales1@xx-insulation.com  
Tel: 86-792-8590828 86-15170255117



3240 ,G-10,G-11,FR-4,FR-5,EPGC308,ESD G10/FR4,EPGM SERIES,UPGM SERIES

## TECHNICAL DATA SHEET

### 3250

Item:	<b>3250 Glass Epoxy Laminate</b>			
Description:	3250 materials are the chemical treatment electrical purposed alkali-free fiberglass reinforced laminates,bonded with high TG epoxy resin.It has high mechanical strength under normal temperature , still has strong mechanical strength , good electrical properties under dry and wet environment, can be used in damp environment and transformer oil.It belongs to class H heat resistance insulating material.			
Standards:	GB/T 1303.2.2009			
Application:	Suitable for class 180 (H) traction motors, large motors as slot wedges and high-end electrical appliances as heat resistant insulation results.			
Availability:	Laminate Sheets:	Thickness	English Units(in) 0.008"-4.0"	SI unites(mm/cm) 0.2-101.6(mm)
		Sheet Size	40" x 48"	102cm x 122cm
			48" x 80"	122cm x 204cm
	48" x 96"		122cm x 244cm	
Fabricated parts:	Xinxing Insulation custom fabricates insulation materials to the exact specifications and drawings of our customers			

#### TYPICAL PROPERTIES OF 3250F CLASS SHEET

Key Characteristic	Units	IEC Requirement	Typical Values	Test Methods
<b>PHYSICAL</b>				
Standard color	--	--	Dark brown <sup>1</sup>	
Density	g/cm <sup>3</sup>	1.8-2.0	1.97	GB/T 1303.2.2009
Water Absorption,24 hrs 3mm	mg	22 max	12	GB/T 1303.2.2009
<b>MECHANICAL</b>				
Flexural strength perpendicular to laminations (under normal condition)	MPa	340 min	614	GB/T 1303.2.2009
Flexural strength perpendicular to laminations (under 180±5℃)	MPa	170 min	440	GB/T 1303.2.2009
Flexural modulus perpendicular to laminations	MPa	--	2.42x10 <sup>4</sup>	GB/T 1303.2.2009
Charpy impact strength parallel to laminations (Notched)	kJ/m <sup>2</sup>	33 min	121	GB/T 1303.2.2009
Tensile strength(MD)	MPa	300 min	459	GB/T 1303.2.2009



Leading Manufacturer of  
ELECTRICAL INSULATION MATERIALS

九江鑫星绝缘材料有限公司  
JIUJIANG XINXING INSULATION MATERIAL CO.,LTD

Email: sales1@xx-insulation.com  
Tel: 86-792-8590828 86-15170255117



3240 ,G-10,G-11,FR-4,FR-5,EPGC308,ESD G10/FR4,EPGM SERIES,UPGM SERIES

Compressive strength perpendicular to laminations (23°C±2°C)	MPa	--	620	GB/T 1303.2.2009
Compressive strength perpendicular to laminations (180°C±2°C)	MPa	--	370	GB/T 1303.2.2009
<b>THERMAL</b>				
Temperature Index	°C	180	180	-
Thermal conductive coefficient (23°C)	W/(m·K)	--	0.432	GB/T 1303.2.2009
Coefficient of linear thermal expansion (30°C-120°C)	10 <sup>-6</sup> /K	--	28.5	GB/T 1303.2.2009
<b>ELECTRICAL</b>				
Electric strength perpendicular to laminations (at 90°C±2°C in oil ), 1mm in thickness	kV/mm	14.2 min	21.3	GB/T 1303.2.2009
Electric strength perpendicular to laminations (at 90°C±2°C in oil ), 3mm in thickness	kV/mm	10.2 min	18.6	GB/T 1303.2.2009
Breakdown voltage parallel to laminations(at 90°C±2°C in oil)	kV	35 min	50 min	GB/T 1303.2.2009
Insulation resistance(after 24h immersion in water)	MΩ	5x10 <sup>4</sup> min	2.5x10 <sup>6</sup>	GB/T 1303.2.2009
Relative Permittivity(50Hz)	--	5.5 max	5.2	GB/T 1303.2.2009
Dielectric dissipation(50Hz)	--	0.04 max	0.0335	GB/T 1303.2.2009
Comparative tracking index	--	200 min	CTI 225	GB/T 1303.2.2009

<sup>1</sup>Custom colors available upon request

The above values are for reference only and are taken from the average test results, and do not represent complete consistency with the actual performance of the material.